
























TECHNICAL CHARACTERISTICS

PURLINE organic flooring | wineo 1000 to glue

Permanently elastic polyurethane flooring according to EN 16776
Without the addition of chlorin, without plasticisers or solvents.

wineo

 to glue	wood L	wood XL	stone L
Format	1298 x 199 mm	1500 x 250 mm	645 x 335 mm
Product thickness	2.2 mm	2.2 mm	2.2 mm
Weight	3.0 kg/m ²	3.0 kg/m ²	3.0 kg/m ²
Planks / m² per box	20 / 5.17 m ²	14 / 5.25 m ²	22 / 4.75 m ²
Boxes / m² per pallet	60 / 310.20 m ²	56 / 294 m ²	66 / 313.50 m ²
Guarantee	Life Time Guarantee for private use according to Windmüller warranty conditions – www.wineo.de		
Classification			Product composition
 Utilization class 23 EN ISO 10874	Domestic area with intensive usage		1 Top element • PU-top layer with surface structure • decor paper • stabilisation
 Utilization class 32 EN ISO 10874	Commercial sector with average usage		
Scratch resistance EN 16776, annex A	Utilization class 23: > 3 N Utilization class 32: > 5 N		
 R9 Anti slip category DIN 51130	R 9		2 Base layer ecuran high performance composite material
 Staining and chemical resistance EN ISO 26987	Very good resistance according to the concentration and residence time		
 Light fastness EN ISO 105-B02	~ 7		3 Backing Integrated Fleece TEC System
 Residual indentation EN ISO 24343-1	≤ 0.10 mm		
 Effect of a furniture leg EN 424	Utilization class 23: Foot type 3 Utilization class 32: Foot type 2 no visible change		
 Castor chair test EN 425	25000 revolutions no damage with rolls type W		
 Thermal resistance ISO 8302	0.01 (m ² K)/W		
 Impact sound reduction EN ISO 10140	~ 4 dB ~ 17 dB in the system with silentPLUS		
 Dimension stability EN ISO 23999	≤ 0.15 %		
 Flexural behaviour EN ISO 24344	≥ 20 mm		
REACH	free from SVHC substances ≥ 0.1 %		
Disposal	<u>Private:</u> possible with normal domestic refuse <u>Commercial:</u> Refuse-key-no. AVV 170203		
 Windmüller GmbH Nord-West-Ring 21 D-32832 Augustdorf DOP: 2001010 EN 14041:2004 / AC2006 1658 www.wineo.de			 www.blauer-engel.de/uz120
 ÉMISSIONS DANS L'AIR INTÉRIEUR A+ Information representative des émissions dans l'air intérieur des substances volatiles présentant un risque de toxicité par inhalation, sur une échelle de classe allant de C (fortes émissions) à A+ (très faibles émissions)			 DGNB NAVIGATOR Registrierungs-Code NAPCCU www.dgnb-navigators.de
 GREENGUARD GREENGUARD GREENGUARD GOLD			 EPD THIRD-PARTY VERIFIED Institut Bauen und Umwelt e.V.
 floor score CERTIFIED BY ICS Global Services			 THE INDOOR CLIMATE LABEL
 Bewertung eco 2 eco-bau			 M1 EMISSION CLASS FOR BUILDING MATERIAL



Relevant Information:

- Underfloor heating: Suitable for all conventional hot water underfloor heating and electrical systems regulated up to a surface temperature of 27 °C.
- Cleaning and care: See separate cleaning & care instruction.
- Technical subjects can be changed by Windmüller GmbH.